



FASSON® 0800


Used to tape and seal joints and seams on fibrous duct boards in the HVAC market

FEATURES:

- High tensile strength aluminum foil facestock
- Specially formulated high tack, antimicrobial acrylic adhesive
- Red lettered / code recognized
- PSA complies with South Coast Air Quality Management District's (SCAQMD) Rule 1168
- UL 181A-P and 181B-FX Recognition under File No. ALKW.MH14352
- · Tested in accordance with UL 723

BENEFITS:

- 20-year Fasson limited product performance warranty
- No costly contractor callbacks
- Ultimate in product reliability
- · Made in the USA



CONSTRUCTION:

Carrier:
Aluminum Foil
Adhesive:
Acrylic
Liner:
Densified Kraft



181A-P / 181B-FX 70P6

LEED® Point Contributor

Contributes to Energy Atmosphere (SA) Credit 1

Contributes to Indoor Environmental Quality (IEC) Credit 4.1



Adhesive Properties:		Typical Values		
Thickness	Test Method(s): PSTC-133	US Mils	MM's	Microns (µm)
_iner:		3.2	0.08	81
Adhesive:		2.4	0.06	61
Carrier:		2.0	0.14	51
Total Caliper:		7.6	0.28	193
PEEL ADHESION	Test Method(s): PSTC-101, AS	TM D-3330, STD-10		
Product 180° 12" min			110.0 //	N1 / 84 - (
Substrate SS	Initial	Lbf / In 5.0	US Oz / In 80	N / Meter 876
		5.0		
LOOP TACK	Test Method(s): PSTC-16, STD	-7		
Product 180° 20" / min			110.0-11	NL / Martan
Substrate SS	Initial	Lbf / In 8.5	US Oz / In 136	N / Meter 1488
STATIC SHEAR Product 1/2" sq (3.25 cm2)	Test Method(s): PSTC-107, AS 2.2 lb (1.0 kg)	TM D 3654, STD-9		
Substrate	2.2 ID (1.0 Ky)	Min to Fail		
SS	Initial	> 10,000		
STATIC SHEAR Aluminum Foil 1" sq (6.5 cm2)	Test Method(s): PSTC-107, AS) 10 lb (4.5 kg)	TM D 3654, STD-9		
Substrate		Min to Fail		-
SS	@ 150°F / 65°C	> 8,000		
	İ			

Product				
Substrate		g / L		
Product		< 15		
	•	•	•	•

TEMPERATURES	° F	° C
Min Application Temp	50 ° F	10 ° C
Max Continuous Operating Temp	350 ° F	176 ° C
Max Intermittent Operating Temp	400 ° F	204 ° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

• It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469