
## POLYKEN®

## Multi-Purpose Duct Tape



| Backing:        | PE Coated Cloth |                                  |  |
|-----------------|-----------------|----------------------------------|--|
| Adhesive:       | Rubber          |                                  |  |
| Liner:          | N/A             |                                  |  |
| Colors:         | Silver, Black   |                                  |  |
| Specifications: |                 | Tested in accordance with UL 723 |  |
| Standard Sizes: |                 | 48mm x 55m, 72mm x 55m           |  |
|                 |                 |                                  |  |

## Applications Sean

- General repair
- General purpose construction uses
- Bundling, patching, and mending
- Seaming and hanging polyethylene sheeting
- Emergency tape for automotive applications

| Features  | Benefits   |
|---|--|
| PE-Coated Cloth Backing                           | <ul> <li>Conforms well to irregular surfaces</li> </ul>      |
|   | Resists twisting and curling                                 |
| <ul> <li>Natural rubber based adhesive</li> </ul> | <ul> <li>High adhesion and holding power for both</li> </ul> |
|   | rough and smooth surfaces                                    |
| Low VOC Content                                   | Can contribute toward satisfying EQ Credit 4.1               |
|   | (Low Emitting Materials) under LEED®                         |

## **Typical Test Values**

|                       | Standard UOM | Metric UOM | Test Method |
|-----------------------|--------------|------------|-------------|
| Total Thickness       | 10.0 mils    | 0.254 mm   | ASTM D-1000 |
| Adhesion to Steel     | 75 oz/in     | 8.21 N/cm  | PSTC-101    |
| Adhesion to Backing   | 43 oz/in     | 4.70 N/cm  | PSTC-101    |
| Tensile Strength      | 24 lb/in     | 42.03 N/cm | ASTM D-1000 |
| Elongation            | 21%          |            | ASTM D-1000 |
| Operating Temperature | 40 to 200 °F | 4 to 93 °C |             |
| VOC Content           | <1 g/L       |            |             |
|                       |              |            |             |

Recommended Storage Conditions: 32-90 °F at 50% RH  $\pm$  2% Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of finess for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.polyken.com